

## ISO Property

starex®

Grade WX-9750

Resin Type ASA

Item	Measuring Method	Condition	Unit	Value
<b>Physical</b>				
Specific Gravity	ISO 1183	Natural or representative color	-	1.07
Melt Flow Index	ISO 1133	220 °C, 10kg	g/10min	4
Mold Shrinkage(MD)	ISO 2577	Flow at 3.2mm(MD)	%	0.6~0.8
Mold Shrinkage(TD)	ISO 2577	X-Flow at 3.2mm(TD)	%	0.6~0.8
<b>Mechanical</b>				
Tensile Strength at Yield	ISO 527	5mm/min	MPa	43
Tensile Strain at break	ISO 527	5mm/min	%	12
Tensile Modulus	ISO 527	5mm/min	MPa	1660
Tensile Strength at break	ISO 527	5mm/min	MPa	32
Flexural Strength	ISO 178	2mm/min	MPa	62
Flexural Modulus	ISO 178	2mm/min	MPa	1950
Izod Impact Strength (notched)	ISO 180 1A	at 23°C, 4mm	KJ/m <sup>2</sup>	41
Charpy Impact Strength (V-notched)	ISO 179 1eA	at 23°C, 4mm	KJ/m <sup>2</sup>	32
Rockwell Hardness	ISO 2039-2	R-scale	-	95
<b>Thermal</b>				
Heat Deflection Temperature(Unannealed)	ISO 75-2	1.8MPa, 4.0mm	°C	77
Heat Deflection Temperature(Unannealed)	ISO 75-2	0.45MPa, 4.0mm	°C	88
VICAT Softening Temperature	ISO R 306	B/50	°C	94

1. The value above is the representative value of the NP or representative color and may have deviation. It can only be used for selecting materials.
2. The value above shall not be regarded as a material specification and cannot be used for molding designs.

Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1) materials, (2) products, and/or (3) design that utilizes recommendations or proposals, of Cheil Industries. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect. Whether materials and/or products of Cheil Industries and/or a design that uses or utilizes Cheil Industries's recommendations or proposals are (is) compatible with individual uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using Cheil Industries's materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.

※ The last update date : 08/02/2013