

OLEXENE PP20 T20 CA

ISSUED: 31/03/2023 ISO 9001 CERTIFIED

OLEXENE PP20 T20 CA is a polypropylene homopolymer injection moulding grade with 20% talc and heat stabilized.

PROPERTIES	CONDITIONS	TEST METHOD	UNITS	VALUES
PHYSICAL PROPERTIES				
Density	23 °C	ISO 1183	g/cm ³	1.04
REOLOGICAL PROPERTIES				
Melt Volume rate	230°C/2.16 kg	ISO 1133	cm ³ /10 min	15
Moulding Shrinkage	longitudinal transversal		%	1.5-1.8 0.9-1.2
PROCESSING CONDITIONS				
Pre-drying conditions	2-4h		°C	80-120
Melt temperature, injection moulding			°C	200-270
Mould temperature			°C	20-80
MECHANICAL PROPERTIES				
Tensile modulus	23 °C, 1 mm/min	ISO 527-1-2	MPa	2800
Tensile strength	23 °C, 50 mm/min	ISO 527-1-2	MPa	35
Elongation at yield	23 °C, 50 mm/min	ISO 527-1-2	%	-
Elongation at break	23 °C, 50 mm/min	ISO 527-1-2	%	5
Flexural modulus	23 °C, 2 mm/min	ISO 178	MPa	2700
Flexural strength	23 °C, 2 mm/min	ISO 178	MPa	50
Charpy unnotched impact strength	23°C -30°C	ISO 179/1eU	kJ/m²	50 -
Charpy notched impact strength	23°C -30°C	ISO 179/1eA	kJ/m²	4 3
THERMAL PROPERTIES				
Melting temperature (DSC)	10°C/min	ISO 3146	°C	163
Heat Deflection Temperature (HDT)	1,8 MPa 0,45 MPa	ISO 75-1-2	°C	70 -

CHARACTERISTICS

OLEXENE PP20 T20 CA is distinguished by high mechanical stiffness, heat stability and easy processing.

APPLICATIONS

OLEXENE PP20 T20 CA is used in a wide range of applications such as housings, automotive, electrical and machinery injection moulded parts.

FORMAT AND STORAGE

Typical formats are Big Bag, octabin and 25kg bags.

The product should be stored in a dry place, protected from light not about 30°C.

NOTE

All recommendations are based on knowledge and experience; The values have been established on standardized tests. The figures should be regarded as guide values and not as binding minimum values. As many factors may affect processing or applications, we recommend that customers make their own tests to determine the suitability of a product for its particular use.

